

Product Description	An extremely durable water-based coating.													
Intended uses	<ul style="list-style-type: none"> • Sealer coating. • Waterproofing compound for walls, parapets, etc. • Coating to bridge small plaster cracks as well as repaired plaster cracks 													
Features & Benefits	<ul style="list-style-type: none"> • Exceptional flexibility • Abrasion resistant • Resistant to oil, diesel, dilute Hydrochloric and sulphuric acid spillage. • Waterproofing compound for walls, parapets etc. • Ready for use 													
Product Information	Appearance	Matt												
	Colour	Off White												
	Volume Solids	50 %												
	Viscosity at 23 °C	500 – 550 grams (KU - paste paddle)												
	Recommended DFT	Brush/roller 200 – 300, Trowel: 1000 µm												
	Recommended WFT	Brush/roller 400 – 600 µm, Trowel: 2000 µm												
	Theoretical spreading rate	2 m ² /L @ 250µm DFT												
	Practical spreading rate	The practical spreading rate will vary depending on the surface profile of the substrate, as well as the application technique and tools used.												
	TVOC	10 g/L												
Application Details	Mixing	Stir thoroughly with a flat paddle until homogeneous before use.												
	Method	Brush, Roller or Trowel.												
	Substrate	Correctly prepared and primed surfaces.												
	Thinning	Thin 5 % for brush and roller application. Trowel application unthinned.												
	Cleaning	Water												
	Drying time	Touch Dry: 1 h @ 23 °C Over coating: 4 h @ 23 °C												
	Application Environment	<table border="1"> <thead> <tr> <th>Surface Temperature</th> <th>Ambient Temperature</th> <th>Relative Humidity</th> </tr> </thead> <tbody> <tr> <td>Min: 10 °C</td> <td>Min: 10 °C</td> <td>Min: 10 %</td> </tr> <tr> <td colspan="3">or 3 °C min. above dew point</td> </tr> <tr> <td>Max: 40 °C</td> <td>Max: 40 °C</td> <td>Max: 85 %</td> </tr> </tbody> </table>	Surface Temperature	Ambient Temperature	Relative Humidity	Min: 10 °C	Min: 10 °C	Min: 10 %	or 3 °C min. above dew point			Max: 40 °C	Max: 40 °C	Max: 85 %
Surface Temperature	Ambient Temperature	Relative Humidity												
Min: 10 °C	Min: 10 °C	Min: 10 %												
or 3 °C min. above dew point														
Max: 40 °C	Max: 40 °C	Max: 85 %												
Storage and Packaging	Store away from direct sun, heat and severe cold. Packaging: 20 L.													
Surface Preparation	Ensure that surfaces are dry, sound, and free from dust, dirt, grease and oil before painting													
	1. NEW WORK													
	1.1 <u>Cement plaster, concrete and porous brickwork:</u> Remove any loose particles and laitance by most suitable means and prime with PROFESSIONAL GYPSUM & PLASTER PRIMER (PP 700) . NB. Soft underbound, friable and highly porous surfaces must be restored to a sound condition with PROFESSIONAL GYPSUM AND PLASTER PRIMER (PP 700) or BONDING LIQUID (CV1 14) .													
	1.2 <u>Fibre cement board:</u> Prime with BONDING LIQUID (CV1 14) .													
	1.3 <u>Mild Steel:</u> Degrease with AQUASOLV DEGREASER (GR 1) . Rinse thoroughly with water. Remove any rust by coarse sanding, mechanical grinding etc. Prime general surfaces the same day with ZINC PHOSPHATE PRIMER (UC 170) or PLASCOSAFE 18 PRIMER (EMS 18) .													
	1.4 <u>Galvanised Iron:</u> Clean with GALVANISED IRON CLEANER (GIC 1) to achieve a water break-free surface. Rinse thoroughly with water. Prime the same day with PLASCOSAFE 18 PRIMER (EMS 18) or METALCARE GALVANISED IRON PRIMER (GIP 1) .													

Surface Preparation Continued	2.	PREVIOUSLY PAINTED SURFACES
	2.1	<p><u>Previously painted surfaces in good condition:</u> Remove loose and flaking paint back to a sound substrate and a firm edge by scraping and sanding. Clean down with POLYCELL SUGAR SOAP POWDER CLEANER solution to remove all contaminants and chalked material. Rinse with clean water to remove all traces of sugar soap. Alternatively, clean with high pressure water jet. Spot prime bare areas with appropriate primer. Sand glossy enamel surfaces to a matt finish and apply one coat of PROFESSIONAL ALL PURPOSE UNDERCOAT (PU 800).</p>
	2.2	<p><u>Previously painted surfaces in poor condition:</u> Completely remove paint by most appropriate means e.g. scraping, coarse sanding or stripping. Wash thoroughly with POLYCELL SUGAR SOAP. Rinse well with fresh water to remove all traces of the cleaning agents and debris. Ensure substrate is sound, not powdery or friable, prior to coating.</p>
	3	<p>FILLING & CRACK REPAIR Fill all imperfections with POLYCELL MENDALL 90 and spot prime filled areas with PROFESSIONAL GYPSUM AND PLASTER PRIMER (PP 700). Repair cracks: <4mm using POLYCELL MENDALL 90, >4mm using POLYCELL MASONRY PATCHING PLASTER. Prime repaired cracks using PROFESSIONAL GYPSUM & PLASTER PRIMER (PP 700).</p>
Application		<ul style="list-style-type: none"> Thin 5 % with water for application by brush or medium pile roller, (Apply at 400-600 µm WFT per coat). Whilst wet smooth out any texture or stipple and taper the edges using a water wet brush. Should this not be done, the profile of the WATERPROOFING COMPOUND (PWC 520) will be visible Trowel: Apply product un-thinned up to 2000 µm WFT or as required Apply 3 coats to window sills, ledges, parapets, plaster bands and protruding plaster detail.
Caution		<ul style="list-style-type: none"> Not to be used for rising or lateral damp. High humidity and low temperatures will retard drying. Avoid painting during inclement weather or if temperature is below 10 °C
Safety Precautions		<ul style="list-style-type: none"> Keep out of reach of children. Ensure good ventilation during application and drying. In case of skin contact, wash with soap and water or a recognised skin cleaner. Avoid contact with eyes – In case of contact, rinse eyes immediately with plenty of water and seek medical advice if symptoms persist. Harmful if swallowed. Do not induce vomiting. Seek medical attention. Refer to Safety Data Sheet for complete information

DISCLAIMER:

The recommendations contained herein are given in good faith and are meant to guide the specifier or the user. They are based on results gained from our tests and experiences and are believed to be reliable. No guarantee is implied by the recommendations contained herein since conditions of use, method of application and cleanliness of the substrate prior to painting are beyond our control.

N.B. Technology may change with time necessitating changes to this Technical Data Sheet (TDS). It is the responsibility of the user to ensure that the latest TDS is being used.

N.B. TO ORDER: Quote product name, product code number, packaging and colour.

KANSAI PLASCON (PTY) LIMITED

10 Frederick Cooper Drive,
 Factoria, Krugersdorp
 South Africa
 1739.
 Tel: +27 11 951 4500
 Fax: +27 800 110 932

PLASCON ADVISORY SERVICE: 0860 20 40 60

EMAIL: advice@kansaiplascon.co.za