



Technical Data Sheet

Date of Issue: 30/09/2022 Revision Date 30/09/2022 | Version 3.0

Product name

STEELTECT 1500 SB CURING AGENT



STRONTIUM CHROMATE EPOXY PRIMER CURING AGENT(KAT 508)

PRODUCT DESCRIPTION

KAT 508 is a pigmented epoxy resin solution

INTENDED USES

- Used to cure STEELTECT 1500 SB(KAT 508)

PRODUCT INFORMATION

Appearance	Pale yellow
Flash Point	<23°C
Viscosity	68 – 84seconds (typical) Ford Cup No. 4

APPLICATION DETAILS

Mixing Ratio	1 part curing agent(KAT 508) to 1 part base(AW 255) by volume	
Mixing	Stir both components separately with a power mixer until homogenous. Add the curing agent to the base and mix thoroughly together. Mix only in proportions shown above. Do not split packs.	
Drying Time	Touch dry	20min at 23°C
	Overcoating (Min)	4h at 23°C
	Overcoating (Max)	7 days at 23°C
	Dry to handle	4h at 23°C
	Full Cure	7 days
Pot Life	6h at 23°C	



STORAGE AND PACKAGING

Store away from direct sun, heat, open flames, sparks and severe cold.

Shelf Life: 24 months(base)
24 months(curing agent)

Dual Packs: 10L unit: 5L in 5L container(base)
5L in 5L container (curing agent)

SAFETY PRECAUTIONS

- Always keep paint out of reach of children.
- Ensure good ventilation during application and drying.
- If accidental contact with skin should occur, wash immediately with soap and water or a recognised skin cleaner.
- Take care to avoid contact with the eyes. In case of contact, immediately rinse the eyes with plenty of water and seek medical attention.
- Harmful if swallowed. Seek medical attention and do not induce vomiting.
- Do not smoke while painting.
- Flammable. Store in a cool dry place away from heat and sparks.
- Refer to Safety Data Sheet for complete information.

DISCLAIMER

The recommendations contained herein are given in good faith and are meant to guide the specifier or the user. They are based on results gained from our tests and experiences and are believed to be dependable. No guarantee is implied by the recommendations contained herein since conditions of use, method of application and cleanliness of the substrate prior to painting are beyond our control.

NB: Technology may change with time necessitating changes to this Technical Data Sheet (TDS). It is the responsibility of the user to ensure that the latest TDS is being used.

NB: TO ORDER: Quote product name, product code number, packaging, and colour.

KANSAI PLASCON (PTY) LTD

10 Frederick Cooper Drive,
Factoria, Krugersdorp
South Africa
1739.

Tel: +27 11 951 4500

Fax: +27 800 110 932

PLASCON ADVISORY SERVICE: 0860 20 40 60

EMAIL: advice@kansaiplascon.co.za